



MAKER SYSTEM EP

Description

These oils are obtained from carefully selected paraffinic bases to which specific additives are added to endow them with marked extreme pressure and anti-wear properties. Therefore, in addition to having a high viscosity index, these oils are highly resistant to oxidation and have excellent demulsifying capacity, easily attaining load step 10 in the FZG test.

These oils are typically used to lubricate bearings by circulation subject to very severe service conditions, including water contamination, normally used in rolling mills.

Their characteristics also make them suitable for lubricating industrial dividers not subject to shock loads, only medium loads.

These oils, despite their EP additives, remain innocuous in the presence of metals, for which they can be used to lubricate large-diameter slow-speed plain bearings by means of drip feed, oil bath or oil ring lubrication. In their lowest level of viscosity, these oils are also used to lubricate medium-speed ball or roller bearings

Properties

- High viscosity index.
- Low pour point.
- Low level of soot.
- Excellent water separation.
- Excellent anti-rust properties.
- Marked extreme pressure properties.

Quality levels, approvals and recommendations

- | | |
|---|---|
| • DIN: 51517/3 - CLP | • ISO: 6743/2 – FC |
| • Load capacity equivalent to that required by DIN 51524 part 2-HLP | • MORGOIL®: MORGOIL® Lubricant Specification; |
| • SMS Group: SN 180-3 | |



MAKER SYSTEM EP

Technical specifications

	UNIT	METHOD	VALUE			
ISO Viscosity Grade			100 EP	220 EP	320 EP	460 EP
Viscosity at 40 °C	cSt	ASTM D445	90	235	320	460
Viscosity at 100 °C	cSt	ASTM D445	10.3	18	24	30
Viscosity index	-	ASTM D2270	95	95	95	95
Density at 15 °C	g/cm3	ASTM D4052	0.886	0.894	0.903	0.903
Flash point, open cup	°C	ASTM D92	230	235	240	265
Pour point	°C	ASTM D97	-9	-9	-9	-9
FZG, load step		DIN 51354	>12	>12	>12	>12
Corrosion Cu, 3hrs 100 °C		ASTM D130	1b	1b	1b	1b
Water separability at 82 °C	min	ASTM D1401	<20	<20	<30	<45
Oxidation resistance, NN at 1000h	mgKOH/g	ASTM D943	<2	<2	<2	<2

The above mentioned characteristics are typical values and should not be considered product specifications.