



## MAKER ANTIX F

### Description

A clear, water resistant oil providing temporary protection against corrosion. Formulated using a natural paraffin base and additives to improve corrosion stability. Antix-F is particularly suitable for inhibiting corrosion in the machining stages of delicate parts. As it is a very light oil, it can be applied using immersion, a brush or a spray gun. It is also suitable for protecting parts and tools that are subject to long periods in storage.

### Properties

- As it is an oily liquid, it does not dry out even when subject to long periods in storage.
- As a result of its liquidity and low interfacial tension, it spreads across the whole surface of the part to be protected, ensuring that it is completely covered.
- Good corrosion inhibitor power thanks to its water repellent additives, which provide a good waterproof film.
- During corrosion tests in a humidity chamber kept at 50% and 100% relative humidity, the oil lasts 45 days without signs of a corrosive attack.
- The oily film deposited is lubricating and need not be removed when undertaking machine or assembly work.
- Does not contain volatile solvents.

### Quality levels, approvals and recommendations

- ISO: 6743/8 - REE

### Technical specifications

	UNIT	METHOD	VALUE
Density at 15 °C	g/mL	ASTM D1298	0.863
Flash point, open cup	°C	ASTM D92	160
Viscosity at 40 °C	cSt	ASTM D445	11
Viscosity at 100 °C	cSt	ASTM D445	3
Viscosity index	-	ASTM D2270	95
Pour point	°C	ASTM D97	-15
TAN	mg KOH/g	ASTM D974	0.25
Saponification index	mg KOH/g	ASTM D94	4

The above mentioned characteristics are typical values and should not be considered product specifications.