



PROTECTOR LITHIUM COMPLEX MOLYB R2 V320

Description

Extreme pressure lithium grease that is specially formulated with a lithium complex thickener. This grease displays excellent performance under extreme conditions, thanks to its extreme pressure additives and 3% molybdenum disulphide content. It also has specific additives to protect equipment against oxidation, high temperatures, and corrosion.

It is highly resistant to water and has excellent adhesiveness, making Molibgras Especial EP 2 ideal for use in wet environments and extreme working conditions.

- Highly recommended for lubricating mechanisms exposed to extreme loads and long greasing periods in the mining and construction industries.
- Lubrication of sleeve bearings, the bearings of hydraulic hammers, open gears, fifth wheels, and front-end loader bolts.
- Can be used in a temperature range of -10°C to 150°C.

Properties

- The carefully-selected small particles of molybdenum disulphide provide additional protection for places that are hard to grease or that may be subjected to extreme conditions while the equipment is being used.
- High mechanical and adhesive resistance.
- Excellent resistance to humidity.
- Good protection against oxidation, corrosion, and rust.

Quality levels, approvals and recommendations

• NEGRI BOSSI: ELEOS, eCANBIO JANUS Y VESTA series*

• DIN: 51502 KPF 2N-10

Technical specifications

| | UNIT | METHOD | VALUE |
|--|---------|------------|-----------------|
| Colour | - | Visual | Black/Gray |
| Consistency | NLGI | | 2 |
| Type of thickener | | | Complex lithium |
| Base oil viscosity at 40 °C | cSt | ASTM D445 | 320 |
| Penetration, 25 °C, 60 strikes worked | 1/10 mm | ASTM D217 | 280 |
| Penetration, 25 °C, 100.000 strikes worked | 1/10 mm | ASTM D217 | 294 |
| Dropping point | °C | ASTM D566 | >260 |
| Corrosion Cu, 24h 100 °C | - | ASTM D4048 | 1a |
| 4 Ball wear, print diameter (1 min/80 kg) | mm | IP 239 | 0.6 |
| 4 Ball EP, welding load | kg | IP 239 | 300 |
| Timken machine load test OK | lb | ASTM D2509 | 45 |

The above mentioned characteristics are typical values and should not be considered product specifications.

^{*}Formal approval